

Technical Data Sheet

BS-2600 / BS-2600S Seal-A-Gap



Features

- ◆ Economical
- ◆ Paintable
- ◆ Permanently Flexible
- ◆ Easy Clean Up

Available Color

- ◆ White

Packaging

- ◆ 450 gm (cartridge)~20/carton
- ◆ 960 gm (sausage)~20/carton

Storage

- ◆ Store in a dry and cool place with temperature below 30 °C.
- ◆ Use within 12 months from date of production.

Product Specification

Base	: Acrylic Latex
Appearance	: Soft Paste
Curing System	: Water Evaporation
Density	: 1.61 gm/ml
Solid content	: 82%
Maximum Tensile Strength (ASTM D412)	: 1.2 N/mm ²
Elongation at Break (ASTM D412)	: 190%
Shore A Hardness (ASTM C661)	: 36
VOC Content (USEPA Method 24)	: 147 gm/L
VOC Content (USEPA Method 310)	: 4%
Working Time (at 25 °C & 50% R.H.)	: <10 Minutes
Application Temperature	: 5°C to 50°C
Service Temperature	: -10°C to 75°C

Description

A one-component, paintable and flexible acrylic sealant formulated for sealing gaps and joints where slight movements or vibration, if occurred, could cause conventional, non-elastic fillers and putties to crack and fall off. It is economical, environmentally friendly, and its adhesion to most porous substrates is good even without primer. It can be cleaned up with water.

Applications

- ◆ General sealing applications: door and window joints, cabinet and wardrobe installation, skirting of wood flooring, etc.
- ◆ Suitable for various substrates: metal, PVC, wood, concrete, gypsum boards, reinforced cement boards, marble, etc.

Application Direction

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Surfaces should be cleaned with alcohol, M.E.K. or other suitable solvent. Do not use soap or detergent.
3. For a neat finish, apply masking tape and remove it before sealant skins over.
4. Cut nozzle at 45° angle to desired bead-width and apply to substrate with cartridge gun.
5. Tool the sealant within 5 minutes of extrusion before it skins.
6. Allow to dry for one hour before applying water-based paint and 24 hours for oil-based paint.
7. Uncured sealant can be cleaned up with damp cloth.

Clean Up

- ◆ Wet sealants can be cleaned up with acetone or mineral spirits.
- ◆ Cured sealants can only be removed mechanically.



BS-2600 Seal-A-Gap

Joint Design

- ♦ The specified sealant bead size should be calculated to comply with the compression and extension capabilities of the sealant in relation to the anticipated joint width due to expansion and contraction.
- ♦ Minimum bead size should not be less than 3 mm to accommodate movement.
- ♦ Sealant design joint width-to-depth ratio should be 2:1.

Limitation

Not recommended for following applications:

- ♦ Below waterline or permanent water immersion.
- ♦ Traffic areas subject to abrasion.
- ♦ Joint movement of more than 10%.
- ♦ Outdoors if it is expected to rain within two hours of sealant application.

Caution

Keep out of reach of children. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.