

Technical Data Sheet

BS-8016BR / BS-8016V7 / BS-801615V Black RTV

**Features**

- ♦ Temperature resistant up to 600 °F (315 °C)
- ♦ Forms leak-proof gaskets in seconds
- ♦ Remains flexible and durable

Available Colour

- ♦ Black

Storage

- ♦ Store in a dry and cool place with temperature below +30°C.

Shelf life:

- ♦ 24 months

Packaging

- ♦ 70 gm (blister card)~144/carton
- ♦ 85 gm (blister card)~144/carton
- ♦ 15 g x 10 (Tube card)~48/carton

Product Specification

Curing System	: Acetoxly
Appearance	: Paste
Odour	: Vinegar-like
Specific Gravity	: 1.02
Tensile at Break	: ≥1.2 MPa
Elongation at Break	: ≥300%
Shore A Hardness	: ≥18
Tack-Free/Skin-Over Time	: ≤25 minutes
Application Temperature	: -20 °C to 50 °C
Service Temperature	: Up to 150 °C

Description

An original gasket maker formulated for heavy duty applications. It makes reliable “formed-in-place” gaskets that resist cracking, shrinking and migration caused by thermal cycling. Ideal to replace almost any cut gasket. Also use to coat pre-cut gaskets to increase reliability. It is permanently flexible and stable at temperature of between -80°F to +600°F (-62°C to +315°C) intermittent. It is also highly resistant to auto shop fluids.

Applications

Rear valve covers, oil pans, timing covers, water pumps, thermostat housing, transmission pans etc.

Directions

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture the tube with the cap and install nozzle.
2. Apply 2-4mm bead to one surface only. Allow the sealant to skin over before assembly.
3. Uncured sealant can be cleaned up with mineral spirits.
4. Replace cap after use and store in cool, dry place.

Caution

This product emits acetic acid whilst curing. Uncured sealant causes skin and eye irritation upon contact. Avoid prolonged contact with eyes or skin. In case of eye contact, flush with water for 15 minutes and seek medical attention immediately. In case of skin contact, wipe off and wash with soap and water. For further health and safety information, consult the latest safety data sheet.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.