

Technical Data Sheet

BS-8130 / BS-8130S Clear RTV Sealant



Features

- ◆ Permanently flexible
- ◆ Durable
- ◆ Indoor and outdoor use

Available Color

- ◆ Clear

Packaging

- ◆ BS-8130 - 75 g(Tube Card) ~ 12/inner; 144/carton
- ◆ BS-8130S - 32 g (Tube Card) ~ 12/inner, 144/carton

Storage

- ◆ Store in a dry and cool place with temperature below 30 °C.
- ◆ Use within 12 months from date of production.

Product Specification

Curing System	: Acetoxy
Appearance	: Paste
Odor	: Vinegar-like
Specific Gravity	: 1.06
Curing Time (t=5mm)	: 2 days
Shore A Hardness	: ≥18
Tensile at Break	: ≥1.2 MPa
Elongation at Break	: ≥300%
Application Temperature	: -20 °C to 50 °C
Service Temperature	: Up to 150 °C

Description

A one component, versatile, acetic cure silicone sealant formulated for general purpose glazing and sealing applications where long term reliability is required. It will bond to form a durable, flexible, waterproof seal on many common wet area building materials. It is suitable for both indoor and outdoor applications.

Applications

It can be used to bond, seal, repair, mend and secure glass, metal, fabric, vinyl, plastics, weather-stripping and vinyl tops.

Direction

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture the tube with the cap and install nozzle.
2. Squeeze tube and push sealant ahead of nozzle to achieve a smooth finish. Sealant skins in 5 minutes, dries to touch in 1 hour and is fully cured in 24 hours.
3. Uncured sealant can be cleaned up with mineral spirits.
4. Replace cap after use and store in a cool, dry place.

Caution

Product releases acetic acid during application and curing. Keep out of reach of children. Use in well ventilated areas. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.