

BOSSIL TECHNOLOGY SDN. BHD.

Technical Data Sheet

BS-8132 Sanitary Sealant Issued date : 31/03/08

Rev. No. : 3

Page

Revised date : 23/05/13

: 1 of 1

Product Specifications:

Physical Properties

Curing system: Oxime **Appearance:** Paste

Odor: Slight unique odor

Specific Gravity:0.985Tack-Free Time:15 - 30 minApplication Temperature:-20 °C to 50 °CService Temperature:-50 to 150 °CShelf life:12 monthsTensile at break JIS K 6249:≥0.8 MPaElongation at break JIS K 6249:≥250%



A one component, mildew resistant silicone sealant formulated for applications in areas where high humidity and temperature may be encountered. It will bond to form a durable, flexible, waterproof seal on many common wet area building materials.



Applications:

Good adhesion on most ceramics, glass and plastics. Widely used for grouting ceramic tiles, bedding tile accessories and sealing shower heads, tubs, rimless, sinks, kitchen and bathroom fixtures.

Directions:

- 1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture the tube with the cap and install nozzle.
- 2. Squeeze tube and push sealant ahead of nozzle to achieve a smooth finish. Sealant skins in 5 minutes, dries to touch in 1 hour and is fully cured in 24 hours.
- 3. Uncured sealant can be cleaned up with mineral spirits.
- 4. Replace cap after use and store in a cool, dry place.

Caution:

Uncured sealant causes skin and eyes irritation upon contact. Avoid prolonged contact with eyes or skin. In case of eyes contact, flush with water for 15 minutes and seek medical attention immediately. In case of skin contact, wipe off and wash with soap and water.

Storage:

- Store in a dry and cool place with temperature below +30°C.
- Use within 12 months from date of production

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company will not accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of various of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.