

BOSSIL TECHNOLOGY SDN. BHD.

Technical Data Sheet

BS-8139 Wet Area Putty Issued date : 31/03/08

Rev. No. : 3

Revised date : 14/05/13

Page : 1 of 2

Product Specifications:

Appearance: Bluish-green paste (Resin)

White paste (Hardener)

Odor: Sulphur-like Main ingredients: Epoxy resin

Polymercaptan hardener

Density: 1.9 g/mL **Lap shear strength:** Minimum 5

(N/mm²) ASTM D1002

Hardness: Minimum 80

(Shore D) ASTM D2240

Working time at 25 °C: < 3 minutes 100% Curing time at 25 °C: 24 hours Non-volatile content: 100%



Product Description:

A fast-setting, fiberglass-reinforced polymer compound that enables permanent repairs to many surfaces including fiberglass, concrete, ceramic, glass, metals, wood and many plastics. It is specially formulated to adhere to surfaces exposed to damp, wet or underwater (salt or fresh) conditions. Each handy stick contains pre-measured portions of activator and base throughout – no measuring or mixing tools are necessary. It contains a fading blue dye and becomes white after mixing. The consistency (like modelling clay) eliminates drips and runs, facilitates adhesion to the substrate and allows the material to be shaped and formed as needed before curing begins. Once cured, it can be drilled, screwed, filed, carved, sanded or painted. It will not shrink or pull away. It is resistant to water, temperature extremes, and chemicals such as hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions and dilute acids and bases.

Applications:

After proper mixing, the epoxy putty molds like clay and may be used to patch dings, scratches, cuts, gouges, and rebuild holes in fiberglass, metal, and wooden boat decks and hulls; to repair fittings, pipes, electrical connections, leaking gaskets, water tanks, fish boxes, marine recreational equipment, tubs, battery cases, sinks, spas, hot tubs, gutters, tanks, pools; to form custom gaskets. It is ideal for repairs to damp wet areas and underwater applications; cures to fiberglass white color. Suitable for interior and exterior use.

Directions:

- 1. Before applying, roughen and clean the area to be repaired.
- 2. Cut or twist off required amount.
- 3. Mix by kneading into a uniform color. If mixing is difficult, warm the epoxy putty to room temperature or slightly higher, or dampen fingers for easier mixing and application.
- 4. As the epoxy putty is mixed, the two contrasting colors will blend into one color to indicate complete mixing.
- 5. Apply to surface to be repaired (within 2 minutes of mixing).
- 6. Force into any cracks or holes and strike off excess material before hardening begins, preferably with a tool wet with clean water.
- 7. When applying to a damp, wet or slowly leaking area, work the material forcefully into the surface and apply pressure until adhesion begins to take effect.

Caution:

Contains epoxy resin and polymercaptan hardener. May cause severe eyes and skin irritation. Avoid prolonged contact with eyes or skin. In case of contact with eyes, flush with water for 15 minutes and seek medical attention immediately. In case of skin contact, wipe off and wash with soap and water. Not intended for use in structural applications. When sanding cured putty and substrate, use protective eye wear and dust mask.

Keep out of reach of children. Use in well ventilated areas.

Storage:



BOSSIL	TECHNOLOGY	SDN. BHD.
--------	-------------------	-----------

Technical Data Sheet

BS-8139 Wet Area Putty Issued date : 31/03/08

Rev. No. : 3

Page

Revised date : 14/05/13

: 2 of 2

Provided the adhesive are stored dry and cool in air tight containers, the storage stability will be at least 12 months (before mixing) from day of delivery.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company will not accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of various of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.

- END -