

	BOSSIL TECHNOLOGY SDN. BHD.	Issued Date: 31/03/08 Revision No: 2 Revision Date: 11/04/13 Page: 1 of 1
	Technical Data Sheet	
	BS-8154 / BS-8156 Liquid Gasket 1101	

Product Specification:

Appearance	Viscous Grey Liquid
Odour	Aromatic Odour
Viscosity (S4, 50rpm)	19000 - 23000 cps
Solids	42 – 44%
Main Solvent	Hydrocarbon Solvent
Main Ingredient	Chloroprene Rubber
Service Temperature	40 °C to 150 °C



Product Description:

Bossil Liquid Gasket 1101 is a semi-drying grey liquid gasket that uses synthetic rubber as the main ingredients. It is formulated to form a layer thick enough to work efficiently on uneven joint surfaces. It exhibits good resistance to heat, oil, gasoline and particularly LPG. It turns into rubber-like elastic substance upon curing.

Applications:

Applications: Ideal for the purpose of making quality gaskets in garages, workshops, homes and Do-It-Yourself.

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture the tube with the cap.
2. Apply a thin layer of the adhesive in uniform manner.
3. Assemble after about 1 minute. Application temperature range is between 40°C to +150°C.
4. Replace cap after use and store in cool, dry place.

Caution:

Avoid contact with eyes, skin and mouth.
 Use in well ventilated area. In case of contact with eyes, flush with water immediately for 15 minutes. If irritation persists, seek medical attention.
 Keep out of reach of children.

Storage:

Highly inflammable, keep away from heat source or naked flames. Store in dry and cool place with temperature below +25°C.
 Use within 12 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of various of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.

- END -